



Sprababbitt C

Physical Properties

Melting Temp (°F)	423
Melting Temp (°C)	217
Density (lbs/in ³)	0.267
Specific Gravity (g/m ³)	7.40
Hardness (HV)	14.1
Specific Heat Capacity (J/Kg)	0.17
Reflow Soldering Temp (°F)	455 - 473
Wave Soldering Pot Temp(°F)	491 - 509

Chemical Specifications

ELEMENT	JSTD-006C (%)
Tin (Sn)	96.0 - 97.0
Silver (Ag)	2.8 - 3.2
Cadmium(Cd)	0.002
Lead(Pb)	0.007
Aluminum(Al)	0.005
Copper(Cu)	0.40 - 0.60
Arsenic(As)	0.03
Iron(Fe)	0.02
Zinc(Zn)	0.003
Gold(Au)	0.05
Indium(In)	0.10
Antimony(Sb)	0.20
Bismuth(Bi)	0.10
Nickel(Ni)	0.01

Additional solder alloys manufactured by GreenGulf

Lead-Free Alloys

Sn99/Ag0.3/Cu0.7
Sn100 (Tin Bar)
Sn95/Sb5
Sn97/3Cu

Leaded Alloys

Sn60/Pb40
Sn62/Pb36/Ag2
Sn30/Pb70
Sn20/Pb80
Sn40/Pb60
Sn63/Pb37 - (SN63)

Limits are % max unless otherwise shown as range or stated otherwise. Except where otherwise indicated, the component elements in each alloy shall deviate from their nominal mass percentage by not > 0.10% of the alloy mass when their nominal percentage is ≤ 1.0%; by not > 0.20% of the alloy mass when their nominal percentage is > 1.0% to ≤ 5.0% or by not > 0.50% when their nominal percentage is > 5.0%.

Main Office
Ulitsa Tankovaya, 89,
Novosibirsk, Novosibirsk
Oblast, Russia 630071

Mailing Address
P.O.Box 288
Novosibirsk, Post No. 630071

P +7941 199 83 62
F +7941 199 83 62
Amy.fan@shgrwt.com
www.greengulf.ltd

Quality Metals Since 1926
ISO Certified Since 1997 / Tin / Tin Alloys / Solder / Nonferrous Metals



APPLICATION

GreenGulf solder bar performs favorably in wave soldering, solder dip, and solder coating applications. For solder plating applications, please refer to GreenGulf ANODES.

BAR SIZE/SHAPE

Standard sizes typically vary by application.

Application	Bar Description	Approx. Weight
Wave (PCB/THT)	KG Bar, Tri-Bar, Feeder Bar	1 lb, 2.2 lbs, 20 lbs

PACKAGING

Packaging can be made to customer specification. Standard packaging is either boxed (25 lbs or 50 lb boxes) or in the case of larger ingots, stacked and wrapped on a pallet. Each box is labeled with the alloy name, lot number, date of manufacture, weight of packaging unit, and any customer specific information required. Each lot will be accompanied by a certificate of analysis showing lot-specific chemistry.

POT MAINTENANCE

In conjunction with the use of GreenGulf solder bar, GF offers a complimentary solder pot analysis program to ensure the user’s application remains at optimal chemistry. In-house OES spectrometers are used for a timely turnaround for customer samples. It is recommended that this program is utilized regularly to verify pot chemistry is within operating specification.

RECYCLING / RECLAIM

Tin Technology and Refining (www.greengulf.ltd) is the recycling/reclaim division of GreenGulf. Tin Tech works in conjunction with GreenGulf solder bar customers to recycle dross, drippings, residues, paste, and other solder scrap that is generated from the use of solder. Tin Tech operates as a permitted, environmentally responsible smelter with full reduction capabilities enabling optimal recoveries for all types of solder scrap material.

STORAGE, HANDLING, SHELF

GreenGulf Solder Bar has an indefinite shelf life when stored in a dry, non-corrosive environment. Bars and packages should always be handled with care as material is naturally heavy.

HEALTH AND SAFETY

This product, during handling or use, may be hazardous to your health. Read the Safety Data Sheet (SDS) and warning label prior to use. SDS can be downloaded from our home page www.greengulf.ltd.

For Sales or Technical Assistance, contact GreenGulf & Co:
Amy.fan@shgrwt.com or +86 16602159378